



**Autex
Acoustics®**

Acoustic
Timber™ Panel™

Manufacturer's
Guarantee

Acoustic Timber™ Panel™ is manufactured by Autex Industries Ltd and Autex Australia Pty Ltd under ISO 9001 and ISO 14001 certified Quality and Environmental Management Systems. The product is guaranteed to be free from manufacturing defects and carries a Manufacturer's Guarantee for a period of no less than ten years to meet all of the performance properties stated within this guarantee.

Specification

| | | |
|---------------------|---|----------|
| Product name | Acoustic Timber™ Panel™ | |
| Description | 100% polyester lightweight semi-rigid panel | |
| | Imperial | |
| Panel dimensions | 4' x 8' | |
| | 4' x 8' 10" | |
| Tolerance | (+0.2") x (+0.4") | |
| Thickness | 1/2" | 1" |
| Tolerance | (+/- 6%) | (+/- 6%) |

**Physical description/
properties**

| | |
|--------------------------|----------------|
| Boiling point: | N/A |
| Melting point: | 482°F |
| Vapour pressure: | N/A |
| Specific gravity: | Polyester 1.38 |
| Flash point: | N/A |
| Explosive limits: | N/A |
| Solubility in water: | Not soluble |
| Alkalinity: | pH 7.8 |
| Relative vapour density: | N/A |

Acoustic performance

Acoustic Timber Panel is made using Cube™ or QuietSpace Panel. The effect of the printed surface has been tested and found to have no impact on the acoustic performance of Cube or QuietSpace Panel.

Minimum Noise Reduction Coefficient 0.45

| Frequency (Hz) | 125 | 250 | 500 | 1000 | 2000 | 4000 | NRC |
|----------------------------------|------|------|------|------|------|------|------|
| ● 1/2" Cube | 0.05 | 0.10 | 0.30 | 0.65 | 0.90 | 0.95 | 0.45 |
| ● 1/2" Cube (with 1" air gap) | 0.05 | 0.30 | 0.60 | 0.95 | 0.95 | 0.85 | 0.70 |
| ● 1" Cube | 0.05 | 0.20 | 0.60 | 0.90 | 1.00 | 1.00 | 0.70 |
| ● 1" Cube (with 1" air gap) | 0.15 | 0.40 | 0.85 | 0.95 | 0.95 | 0.95 | 0.80 |
| ● 1" QuietSpace | 0.15 | 0.45 | 0.85 | 1.00 | 1.00 | 0.95 | 0.85 |



Product specifications

Fire ratings

Acoustic Timber is made from Cube™ which has been tested and evaluated using the following test methods:

ISO 9705: 1993

Classification: Group 1-S

Smoke production rate:

<5.0m²/s

As required by NZBC C/VM2

AS ISO 9705 - 2003

Classification: Group 1

(SMOGR_{ARC}): <100m²/s²

Assessed using methodology AS ISO 9705 - 2003 in accordance with AS 5637:2015, as required by BCA Specification C110-4
FI 4974
FAR 4055

BS EN 13501-1:2018

Wall applications

Classification: B-s₂d₀

(Cube™ 1/2")

Tested using BS EN ISO 11925-2:2020 and BS EN 13823:2020 and classified in accordance with BS EN 13501-1:2018, as required by BS EN 15102:2007 + A1:2011. EUI-20-000268-A

Wall applications

Classification: B-s₂d₂

(Cube™ 1")

Tested using BS EN ISO 11925-2:2020 and BS EN 13823:2020 and classified in accordance with BS EN 13501-1:2018, as required by BS EN 15102:2007 + A1:2011.
EUI-21-000135-G-A

Wall applications

Classification: B-s₂d₂

(1" Quietspace® Panel)

Tested using BS EN ISO 11925-2:2020 and BS EN 13823:2020 and classified in accordance with BS EN 13501-1:2018, as required by BS EN 15102:2007 + A1:2011. EUI-21-000135-E-A

Ceiling applications

Classification: B-s₂d₀

(Cube™ 1/2")

Tested using BS EN ISO 11925-2:2020 and BS EN 13823:2020 and classified in accordance with BS EN 13501-1:2018, as required by BS EN 13964:2014.
EUI-20-000268-B

Ceiling applications

Classification: B-s₂d₂

(Cube™ 1")

Tested using BS EN ISO 11925-2:2020 and BS EN 13823:2020 and classified in accordance with BS EN 13501-1:2018, as required by BS EN 13964:2014.
EUI-21-000135-G-B

Ceiling applications

Classification: B-s₂d₂

(1" Quietspace® Panel)

Tested using BS EN ISO 11925-2:2020 and BS EN 13823:2020 and classified in accordance with BS EN 13501-1:2018, as required by BS EN 13964:2014.
EUI-21-000135-E-B

ASTM E-84-15a

Class A, FS:0 - SD:45 (Cube™ 1/2")
RJ4479

Class A, FS:0 - SD:65

(Cube™ 1")

RJ4479

ASTM E-84-15a

Class A, FS:0 - SD:45

(Cube™ 1/2")

RJ4479

Class A, FS:0 - SD:65

(Cube™ 1")

RJ4479

Suitable applications

Suitable for use as acoustic and decorative treatments in non-contact areas.

For applications where contact is likely to occur, Autex Acoustics recommends our standard Cube™ or Quietspace® Panel range.

Acoustic performance

The ink used to print this surface finish has been tested and found to have no impact on the acoustic performance of Autex Acoustics® products. Please contact your account manager for further information if required.

Impact resistance

Acoustic Timber may show surface damage when subjected to impacts.

We would advise against using Acoustic Timber in areas where there is likely to be contact with the product.

VOC emissions

Acoustic Timber has been tested for chemical emissions in accordance with ASTM D5116 and is considered a low VOC and low formaldehyde emissions product. VOC emissions: 0.019 mg/m³ Formaldehyde emissions: <0.005 mg/m³

Color fastness to light

Acoustic Timber is suitable for indoor use only. Light fastness is dependent on use and exposure. Acoustic Timber has been evaluated to the following standard: ISO 105-B02:2014
Rating: 6 (Highest = 7)

Light Reflectance Value (LRV) solid colors

When selecting Acoustic Timber, a sample can be provided and tested for LRV. Please contact

your account manager at the start of your project to arrange a test.

Fabric care

Avoid contact with the Acoustic Timber surface. Where liquids and other contaminants come in contact with the panels, these should be gently removed immediately and not allowed to soak-in, dry, or set. Refer to the product Care and Maintenance Guide for cleaning guidance. Consult a specialist cleaning company for cleaning if required.

Finish

The acoustic product color may vary from samples and between each product batch. This is due to the inherent nature of the textile. This will not affect the color of the Acoustic Timber. It is not recommended to pin Acoustic Timber as the printed surface finish is not self-healing, the backing panel color may be visible if pinned.

Blemishes

Due to the nature of the raw material and the manufacturing process, flecks and other small surface blemishes may be visible on the surface of Autex Acoustics panels from time to time. This is an inherent characteristic of the textile products and is unavoidable.

Service

For further information about Acoustic Timber or any other Autex Acoustics product, please contact your account manager or visit our website. The information contained in this document is correct to the best of our knowledge at the date of its publication. It is the user's responsibility to determine if this information is suitable for their intended application and to make sure that this document is the most current publication. You can do this by checking our website or contacting your account manager.

Care and maintenance

Maintain in accordance with the Care and Maintenance Guide available for this product.

● New Zealand

702-718 Rosebank Road,
Private Bag 1998
Avondale 1746, Auckland
New Zealand
Freephone 0800 428 839
Phone +64 9 828 9179
Fax +64 9 828 5810

● Australia

285 Swan Street,
Richmond, VIC 3121,
Australia
Freephone 1800 678 160
Phone +61 3 9450 6700

● United Kingdom

Unit J4, Lowfields Way,
Lowfields Business Park,
Elland, West Yorkshire
HX5 9DA
United Kingdom
Phone +44 0 142 241 8899

● United States

1630 Dan Kipper Drive,
Riverside, CA 92507
United States of America
Phone +1 424 203 1813

Autex is an ISO certified organisation encompassing Quality (ISO 9001), Environmental (ISO 14001), and Health and Safety (ISO 45001). Brand names and logos are registered or unregistered trademarks owned or used under license by Autex Industries Limited or other members of the Autex Group. © Copyright 2022 Autex Industries Ltd. All rights reserved. It is the user's responsibility to determine if the product and information presented in this document is suitable for the intended application by engaging a suitably qualified consultant. The information contained in this document is correct to the best of our knowledge at the date of its publication. To verify that this document is the most current publication please check our website or contact your Autex account manager.